

Shadow bands in overdoped $Bi_2Sr_2CaCu_2O_{8+x}$

S. La Rosa¹, R.J. Kelley², C. Kendziora³, G. Margaritondo¹, M. Onellion² and A.
Chubukov^{2,4}

¹ *Institut de Physique Appliquee, Ecole Polytechnique Federale Lausanne, Switzerland*

² *Physics Department, University of Wisconsin, Madison, WI 53706*

³ *Naval Research Laboratory, Washington, D.C.*

⁴ *P.L. Kapitza Institute for Physical Problems, Moscow, Russia*

(today)

Abstract

We performed angle-resolved photoemission experiments on overdoped single crystal $Bi_2Sr_2CaCu_2O_{8+x}$ samples with T_c values as low as 55K and very narrow transitions as measured by AC susceptibility. The photoemission data indicate the presence of a “shadow” peak in the quasiparticle spectral function $A(\omega)$ shifted by (π, π) from the conventional quasiparticle peak. The ratio of the shadow/quasiparticle peak amplitudes strongly increases with the binding energy. This is consistent with the idea that the shadow peak is not a structural replica of the quasiparticle peak, but rather a maximum in a spectral function which can exist due to interaction with spin fluctuations peaked at (π, π) .

The question of what boson mediates the superconducting pairing interaction is of great interest in high-temperature superconductors. Alternatives to phonons include spin fluctuations [1]. The exchange by spin fluctuations peaked at antiferromagnetic momentum $Q = (\pi, \pi)$ yields a d -wave pairing state which is consistent with a number of experiments on high- T_c materials. However, there are restrictions which have to be met in order to have strong attraction in a d -wave channel: (i) spin fluctuations should be peaked at or very near Q ; (ii) one should be able to find a region of fermionic momentum along the directions where the d -wave gap has a maximum, where k and $k + Q$ are both located near the Fermi surface; (iii) in the density of states, there should be no precursors of the upper and lower bands of the magnetically ordered state - otherwise vertex corrections would strongly decrease pairing interaction [2]. Near optimal doping, neutron scattering [3], and photoemission experiments [4] and numerical studies of the density of states [5] indicate that all three conditions are satisfied.

An open issue is whether the weak peak at $k = Q$ in the dynamical susceptibility observed at optimal doping means that spin fluctuations are strong enough to yield T_c values consistent with experiment. In photoemission studies, a way to check whether or not spin fluctuations are relevant is to study the form of $A(k, \omega)$ for $k \approx k_F + Q$ where k_F is the (angle dependent) Fermi momentum. If spin fluctuations at optimal doping are still strong, then $A(k)$ measured at a given *small* frequency should have a second maximum at $k = k_F + Q$ due to singular self-energy corrections [6]. An important distinction is that this second peak in $A(k)$ is not a second quasiparticle peak but just an enhancement of the low-frequency part of the spectral function. In this sense, the situation at optimal doping is qualitatively different from that at and very near to half-filling where the valence and conduction bands are almost preformed. In the latter case, $A(\omega)$ measured at $k \approx k_F$ and $k_F + Q$ should behave nearly in the same way, i.e., the photoemission data should reveal two *quasiparticle* peaks separated by Q [7]. In fully doped materials, however, the spectral weight is transformed from the conduction to the valence band, and the second quasiparticle peak should disappear; when and how this happens, however, depends on the details of the electronic structure.

The momentum dependence of the spectral function in *Bi2212* at the smallest possible frequency has been measured by Aebi et al. [8]. They reported observing a second, shadow peak, but have been careful to note that it is an open question whether this peak is due to antiferromagnetic fluctuations or it merely reflects the presence of the structural replica of the Fermi surface and the quasiparticle band.

In this communication we report on measurements of the relative intensity of the shadow peak and the main quasiparticle peak as a function of the binding energy. These measurements distinguish between magnetic and structural origins of the shadow peak. The reason is as follows. If the shadow peak is the structural replica of the quasiparticle peak, it should have the same Fermi-liquid frequency dependence at the lowest frequencies, $A(\omega) \propto \omega^{-2}$, as the main peak, and the ratio of the two should be virtually independent on frequency. If, on the contrary, the second peak is just an enhancement of the low frequency part of $A(\omega)$ at $k_F + Q$ due to spin fluctuations, then the relative intensity of the shadow peak should vanish when binding energy tends to zero.

We have studied overdoped *Bi₂Sr₂CaCu₂O_{8+x}* single crystals, with transition temperatures, $T_c=55-62K$ and report observing shadow peaks using conventional angle-resolved photoemission spectroscopy in which one measures spectral function as a function of frequency at a given momentum. We found that the relative intensity of the shadow peak strongly increases with increasing binding energy which agrees with the idea that the shadow peak is not a second quasiparticle peak.

Single crystal samples of *Bi₂Sr₂CaCu₂O_{8+x}* were grown using a self-flux technique in a strong horizontal thermal gradient to stabilize the direction of solidification.[10,11] The individual crystals were manually separated from the bulk charge utilizing their propensity to cleave micaciously perpendicular to the crystallographic *c*-axis. Typical dimensions for samples in this study were $4mm \times 4mm \times 30um$, with the shortest length along the *c*-axis.

Our AC susceptibility measurements have shown that the crystals exhibit a 10 – 90% transition in a T range of $0.5K$ for both optimally doped and overdoped samples. Previous reports [9] indicated a best transition width of $1.3K$ for optimally doped material and $3K$

for somewhat overdoped samples ($T_c=72-75K$). The narrow transition width indicates a more homogeneous oxygen and cation doping than in earlier studies. Fig. 1 illustrates AC susceptibility measurements of overdoped and optimally doped $Bi_2Sr_2CaCu_2O_{8+x}$ single crystals. There is no indication of either $Bi_2Sr_2CuO_{6+x}$ or $Bi_2Sr_2CaCu_3O_{10+x}$ phases. This is confirmed by x-ray diffraction and resistivity measurements, as reported in detail elsewhere [10].

Angle-resolved photoemission measurements were performed using a 50mm radius hemispherical electron energy analyzer, mounted on a two-axis goniometer. The samples were transferred from a load lock chamber to the ultrahigh vacuum photoemission chamber (base pressure 6-7E-11 torr). The samples were cooled to just above their superconducting transition temperature of $55 - 62K$ and cleaved while cold. The sample orientation with respect to the sample surface normal was adjusted in situ and confirmed using low energy electron diffraction [11]

Fig. 2 illustrates angle-resolved photoemission spectra taken along the $\Gamma - X(k_x = k_y)$ and $\Gamma - Y(k_x = -k_y)$ directions in the Brillouin zone, for both cases we plotted the data for an overdoped sample with $T_c = 55K$. Several noteworthy points emerge from the data. First, the main Fermi surface crossing, at $(0.38 \pm 0.01)Q$, occurs at a slightly smaller wavevector than that for optimally doped or slightly overdoped samples [12], because our samples have a higher carrier concentration. Second, we found another peak in the photoemission intensity, that appears at our smallest frequency at $(0.64 \pm 0.02)Q$. Within our experimental error, this second peak is located exactly at a distance $Q = (\pi, \pi)$ from the Fermi surface, i.e., it is a shadow peak. As the wavevector is increased further from $0.64Q$, the shadow peak disperses towards higher binding energies. By a wavevector of $0.75Q$, the peak, now very weak, is at a binding energy of 180-200 meV.

We reproducibly observed these new features of the photoemission spectra on three different samples and in both the $\Gamma - X$ and $\Gamma - Y$ directions. Including looking at more than one angular cut on some samples, we looked for, and found shadow peaks in a total of eight angular cuts. Our results obtained on different samples are presented in Fig. 3.

The main Fermi surface measured by P. Aebi et.al. is shown by a solid line, the location of the shadow peak by a dotted line, and our experimental results by open circles. The Fermi surface wavevectors obtained for all three samples are, within our experimental error, the same, so the same open circle symbol is used for all samples. The strength of the intensity at the shadow peaks is polarization-dependent; the details of this will be reported elsewhere [13].

Fig. 4 illustrates the ratio, R , of the shadow peak/ main quasiparticle peak amplitudes as a function of binding energy. Data were obtained from six angular cuts on four samples. The ratio increases as the binding energy increases; the increase is as much as by a factor of 4.2. It is very unlikely that such increase can be explained if one assumes that the shadow peak is just a structural replica of the quasiparticle peak. A more realistic conclusion from the data is that there is just one Fermi surface, located at k_F , one band of propagating quasiparticle excitations near k_F , while the shadow peak is just an anomaly in the spectral function. This conclusion also agrees with our experimental observation that the increase of the shadow peak/main peak amplitude ratio is primarily due to the decrease of the main peak amplitude as binding energy increases; the amplitude of the shadow peak demonstrates only weak dependence on the binding energy.

As we already mentioned, the existence of the second peak in $A(k, \omega \rightarrow 0)$ located at $k_F + Q$, can be explained as due to the interaction with spin fluctuations. The exchange of spin fluctuation yields fermionic self-energy $\Sigma(k, \omega) = g^2 \int d\vec{q} d\Omega G_0(k + q, \omega + \Omega) \chi(q, \Omega)$, where g is the coupling constant, $G_0(k, \omega) = \omega - (\epsilon_k - \mu) + i\delta \text{sgn}\omega$ is the Green function for free fermions (ϵ_k is an excitation energy and μ is the chemical potential). The magnetic susceptibility $\chi(q, \Omega)$ describes overdamped spin excitations and is assumed to be peaked at Q . The low-energy part of $\chi(q, \Omega)$ is well approximated by $\chi^{-1}(q, \Omega) \propto (\Delta^2 + v^2(q - Q)^2 + 2i\gamma\Omega)$ [14], where γ (the damping term) and v are of the order of the electronic bandwidth, W , and Δ is the gap which vanishes at the antiferromagnetic transition point. The near antiferromagnetism implies that $\Delta \ll W$.

Consider now a region of k values which are close to the shadow point $k_F + Q$, but are

relatively far from k_F such that $\epsilon_k - \mu = O(W)$. In this situation, $A(k, \omega) \propto \text{Im}\Sigma(k, \omega)$. Now, the key point is that the self-energy is nearly singular for $k = k_F + Q$ and $\Delta \ll W$, and this near singularity gives rise to a maximum in $A(k)$ at $k = k_F + Q$. The full expression for the low-frequency part of $\Sigma(k, \omega)$ was obtained in [6,15], and here we present only the results for several limiting cases. For $\Delta = 0$, we have

$$A(k, \omega) \propto \frac{\omega^2}{(\epsilon_{k+Q} - \mu)^3}$$

for $\omega < (\epsilon_{k+Q} - \mu)^2/\omega_0$ ($\omega_0 = O(W)$), and

$$A(k, \omega) \propto \omega^{1/2}$$

for $\omega > (\epsilon_{k+Q} - \mu)^2/\omega_0$. Clearly, $A(k)$, measured at a given, small ω has a maximum when $\epsilon_{k+Q} = \mu$, i.e., $k = k_F + Q$. For $\Delta \neq 0$, the behavior is more complex, but the peak in $A(k)$ at $k = k_F + Q$ survives as long as $\Delta \ll W$.

The above arguments can be applied to the experiments of Aebi et al., who measured $A(k)$ at a given frequency. The present experiments were performed in a different way: the photoemission spectra were obtained as functions of the binding energy (i.e., frequency) for several values of k . The location of the shadow peak was obtained as the position of the maximum of $A(\omega)$ at a given k . To account for these data, the low-energy spin-fluctuation approach has to be modified because in the present form, it allows one to predict only the form of $A(\omega)$ when it increases as a function of frequency. At larger frequencies, $A(\omega)$ indeed passes through a maximum and then decreases. However, to find the self-energy in this frequency range, one has to utilize the sum rule for the susceptibility which in turn requires one either to add higher powers of frequency and momentum into the expression for susceptibility or introduce a cutoff in the momentum/frequency integration over bosonic variables. In both cases, the maximum of $A(\omega)$ is expected to be located at some frequency compared to ω_0 which apparently does not depend crucially on how close k is to $k_F + Q$. The amplitude of $A(\omega)$ near the maximum is also expected not to depend strongly on $\epsilon_{k+Q} - \mu$. In other words, within weak coupling spin-fluctuation approach

(when coupling is small enough to yield a pseudogap), only the low-frequency part of $A(\omega)$ changes drastically around $k = k_F + Q$, while the rest of $A(\omega)$ doesn't change much. The near independence of the shadow peak amplitude on the binding energy is consistent with experiment - the shadow peak amplitude does demonstrate some frequency dependence with the maximum at $\omega = 70 - 90 \text{ meV}$, but the maximum observed change in the amplitude is much less than that of the main band, by a factor of (x3.3) or greater. In Fig. 4 we fitted the data for the amplitude ratio by an ω^2 dependence which would be the case if the shadow peak was completely ω independent, while the main peak follow the Fermi-liquid prediction $A(\omega = \epsilon_k - \mu) \propto \omega^{-2}$. We see that at small frequencies, the fit works reasonably well, but there are deviations at higher frequencies as expected due to higher-order terms in the frequency expansion.

At the same time, the observed strong variation of the shadow peak location with the deviation from $k_F - Q$ cannot presently be explained within the weak-coupling spin-fluctuation approach. One possibility is that already in a weak-coupling spin-fluctuation theory, the position of the peak in $A(\omega)$ in fact does have some moderate k dependence as a result of the interplay between the parameters in spin susceptibility and electronic dispersion. Another possibility is that some features of the strong-coupling, almost spin-density-wave solution [16], specifically the existence of a second, propagating quasiparticle pseudoband, can still be observed at not very small frequencies even in the overdoped case.

To conclude, in this paper we reported the observation of the shadow peaks in photoemission studies of overdoped 2212Bi samples. We studied the relative intensity of the shadow and main peaks and found that it strongly increases with frequency. This indicates that the shadow peak is not a structural replica of the main peak, but rather an enhancement of the spectral function at $k \approx k_F + Q$. This enhancement may be due to the interaction with spin fluctuations, and our data thus provide some support to the idea [1] that spin fluctuations remain peaked at (π, π) even in the overdoped regime. That is, even highly overdoped samples appear to support a paramagnon as a possible exchange boson involved in superconductivity. On the other hand, the shadow peak exhibits a strong k -dependence

of the peak position. Within the spin-fluctuation model, we cannot presently provide a definitive explanation for this observation.

We benefitted from conversations with Philippe Aebi, Ivan Bozovic, Robert Joynt and Igor Mazin. Financial support was provided by the U.S. NSF, both directly and through support of the Wisconsin Synchrotron Radiation Center, Ecole Polytechnique Federale Lausanne, and the Fonds National Suisse de la Recherche Scientifique. SLR is an EC Fellow, C.K. is a National Research Council Fellow, and A.C. is an A.P. Sloan Fellow.

REFERENCES

- [1] P. Monthoux and D. Pines, Phys. Rev. B **47**, 6069 (1993); *ibid* **50**, 16015 (1994).
- [2] J.R. Schrieffer, J. Low Temp. Phys. **99**, 397 (1995); A. Chubukov, D. Morr and K. Shakhnovich, Phil. Mag., to appear.
- [3] see e.g. H. Mook et al, Phys. Rev. Lett. **70**, 3940 (1993); B.J. Sternlieb et al, Phys. Rev B **47**, 5320 (1993); H.F. Fong et al, preprint.
- [4] R. Liu et al, Phys. Rev. B **45**, 5614 (1992); **46**, 11056 (1992); D.S. Dessau et al, Phys. Rev. Lett **71**, 2781 (1993).
- [5] E. Dagotto, F. Ortolani and D. Scalapino, Phys. Rev. B, **46**, 3183 (1992); S. Haas, E. Dagotto and A. Moreo, Phys. Rev. Lett, **74**, 4281 (1995); R. Preuss, W. Hanke and W. von der Linden, Phys. Rev. Lett. **75**, 1344 (1995).
- [6] A.V. Chubukov, Phys. Rev. B, **52**, R3847 (1995).
- [7] A.P. Kampf and J.R. Schrieffer, Phys. Rev B **42**, 7967 (1990); see also S. Chakravarty, Phys. Rev. Lett **74**, 1885 (1995).
- [8] P. Aebi et al, Phys. Rev. Lett **72**, 2757 (1994); *ibid* **74**, 1886 (1995).
- [9] R.J. Kelley et al, Phys. Rev. B **48**, 3534 (1993).
- [10] C. Kendziora et al, Physica C, in press.
- [11] R.J. Kelley et al, Phys. Rev. Lett **71**, 4051 (1993).
- [12] Jian Ma et al, Phys. Rev. B **51**, 3832 (1995); *ibid* **51**, 9271 (1995).
- [13] S. LaRosa et al, unpublished. We had previously performed such measurements without conclusively observing shadow peaks. The present samples are more homogeneously oxygen doped; the susceptibility width is a factor of ($\times 3 - \times 5$) more narrow, making it easier to observe weak signal from shadow peaks.

- [14] A. Millis, H. Monien and D. Pines, Phys. Rev. B **42**, 197 (1990); V. Barzykin et al, *ibid* **49**, 1544 (1994); V. Barzykin and D. Pines, Phys. Rev. B , to appear.
- [15] A.J. Millis, Phys. Rev. B **45**, 13047 (1992); L.B. Ioffe, A.I. Larkin, A.J. Millis and B.L. Altshuler, JETP Lett., **59**, 65 (1994).
- [16] J.R.Schrieffer, X.G.Wen, and S.C.Zhang, Phys. Rev. B **39**, 11663 (1989); A.V.Chubukov and D.M.Frenkel, *ibid* **46**, 11884 (1992).

FIGURES

FIG. 1. AC susceptibility measurements of optimally doped, as grown, and overdoped samples. The 10 – 90% transition width is $0.5K$ for all samples studied

FIG. 2. (a) Series of photoemission energy distribution curves (EDC's) versus location in the Brillouin zone along the (π, π) direction. Inset illustrates location in Brillouin zone at which each spectrum was taken. (b) Corresponding EDC's for the $(\pi, -\pi)$ direction. Note the appearance of a shadow peak for both directions.

FIG. 3. Location of main Fermi surface crossing and a shadow peak nearest to the Fermi energy (open circles), obtained from a series of data like as in Fig. 2. Solid line is Fermi surface for optimally doped samples. Dotted line is shadow peak observed in Ref. [8] for optimally doped samples. Samples are more overdoped than Ref. [8], so the main crossing is closer to the center of the Brillouin zone. The shadow peaks are shifted from the main peaks by (π, π) .

FIG. 4. Ratio R of shadow peak/main quasiparticle peak amplitudes as a function of binding energy E_b , taken from a series of data like as in Fig. 2. The ratio R has been normalized to 1.0 at lowest binding energy (45 meV). Open circles are data taken on three different samples. Dotted line is the result expected if the shadow peak is structural in origin. Solid line is the result expected if the shadow peak is due to short-ranged spin fluctuations.